Q-LAB

INSPECTION REPORT

Q-Lab Weathering Research Service

TEST NO: AAM-0002

REPORT NO: 1A

DATE: July 13, 2004

Specimen Number					No. of chips			Chip Rating	Chip Size	Notation	Failure Type	Levels of failure
Room temperature												
1						29		5B	1-3mm	T	Cohesional	Topcoat*
2						44		5B	1-3mm	T	Cohesional	Topcoat*
3						43		5B	1-3mm	T	Cohesional	Topcoat*

Q-Lab Florida: 1005 SW 18th Avenue • P.O. Box 349490 • Homestead, FL 33034 • Telephone: 305-245-5600 • Fax: 305-245-5656 • E-mail: q-lab@q-panel.com

Q-PANEL LAB PRODUCTS